



**ŞİŞECAM
KUM**

S3-35-250

ÜRETİM YERİ: ÇATALCA - YALIKÖY

KİMYASAL ÖZELLİKLERİ (%):

SiO ₂	99,0 ± 0,2
Al ₂ O ₃	0,45 ± 0,2
Fe ₂ O ₃	0,035 ± 0,02
TiO ₂	0,1 ± 0,1
CaO	0,02 ± 0,01
MgO	0,02 ± 0,02
Na ₂ O	0,01 ± 0,01
K ₂ O	0,1 ± 0,1
L.O.I	0,1 ± 0,1

TANE BOYUTU (%):

+1000 µ	0,0
-1000 +500 µ	2,0 max.
-500 +300 µ	
-500 +250 µ	
-300 +106 µ	
-250 +106 µ	
-106 µ	55,00 min.
< 45 mikron	

RUTUBET (%):

7,0 max.

AMBALAJ:

Dökme

ŞİŞECAM KİMYASALLAR

İçmeler Mahallesi D-100 Karayolu Cad.
No: 44B 34947 Tuzla / İstanbul / Türkiye

T +90 850 206 30 14

www.sisecamkimyasallar.com



ŞİŞECAM SILICA SAND

S3-35-250

PLACE OF PRODUCTION: ÇATALCA - YALIKÖY

CHEMICAL CONTENT (%):

SiO ₂	99,0 ± 0,2
Al ₂ O ₃	0,45 ± 0,2
Fe ₂ O ₃	0,035 ± 0,02
TiO ₂	0,1 ± 0,1
CaO	0,02 ± 0,01
MgO	0,02 ± 0,02
Na ₂ O	0,01 ± 0,01
K ₂ O	0,1 ± 0,1
L.O.I	0,1 ± 0,1

PARTICLE SIZE (%):

+1000 µ	0,0
-1000 +500 µ	2,0 max.
-500 +300 µ	
-500 +250 µ	
-300 +106 µ	
-250 +106 µ	
-106 µ	55,00 min.
< 45 mikron	

MOISTURE (%):

7,0 max.

PACKING:

Bulk

ŞİŞECAM CHEMICALS

İçmeler Mahallesi D-100 Karayolu Cad.
No: 44B 34947 Tuzla / Istanbul / Turkey

T +90 850 206 30 14

www.sisecamchemicals.com